

Segmento: Barita - Petróleo & Gás, Pastilhas de Freio e Argamassa



CARACTERÍSTICAS TÍPICAS · TYPICAL CHARACTERISTICS	PROBARI 10	PROBARI 20
DENSIDADE ESPECFICA DENSITY g/cm ²	4.10 min	4.20 min
RETENÇÃO EM 74 m (200 Mesh) RESIDUE GREATER THAN 74 m (200 Mesh) - %	3.00 max.	3.00 max.
BaSO ₄ - %	80.00 min.	90.00 min.
CÁDMIO CADMIUM	3 ppm max.	3 ppm max.
MERCÚRIO MERCURY	1 ppm max.	1 ppm max.
UMIDADE MOISTURE - %	1.00 max.	1.00 max.
Fe - %	5.00 max.	3.50 max.
Si - %	5.00 max.	3.50 max.